

# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

### Product Information

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

**Zytel® E51HSB NC010 is a high molecular weight, heat stabilized polyamide 66 resin for injection molding and extrusion.**

General information	Value	Unit	Test Standard
Resin Identification	PA66	-	ISO 1043
Part Marking Code	PA66	-	ISO 11469
Rheological properties	dry / cond	Unit	Test Standard
Viscosity number	310 <sup>(1)</sup> / *	cm <sup>3</sup> / g	ISO 307, 1157, 1628
Molding shrinkage, parallel	1.3 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3 / -	%	ISO 294-4, 2577
1: 90% formic acid			
Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	3100 / 1200	MPa	ISO 527-1/-2
Yield stress	84 / 55	MPa	ISO 527-1/-2
Yield strain	4.3 / 29	%	ISO 527-1/-2
Nominal strain at break	35 / -	%	ISO 527-1/-2
Strain at Break, 23°C, 50mm/min	>50 / -	%	ISO 527-1/-2
Flexural Modulus	2800 / -	MPa	ISO 178
Charpy impact strength, 73°F	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength			ISO 179/1eA
73°F	7 / 21	kJ/m <sup>2</sup>	
-22°F	6 / 4	kJ/m <sup>2</sup>	
Izod notched impact strength, 73°F	6 / -	kJ/m <sup>2</sup>	ISO 180/1A
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature, 18°F/min	262 / *	°C	ISO 11357-1/-3
Temp. of deflection under load			ISO 75-1/-2
260 psi	70 / *	°C	
65 psi	200 / *	°C	
Vicat softening temperature, 90°F/h, 11 lbf	221 / *	°C	ISO 306
Coeff. of linear therm. expansion, parallel	100 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.16	W/(m K)	-
Spec. heat capacity of melt	2790	J/(kg K)	-
Flammability	dry / cond	Unit	Test Standard
Oxygen index	20 / *	%	ISO 4589-1/-2
FMVSS Class	DNI	-	ISO 3795 (FMVSS 302)
Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	>1E13 / 1E11	Ohm*m	IEC 62631-3-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties	dry / cond	Unit	Test Standard
Humidity absorption, 80mil	2.6 / *	%	Sim. to ISO 62
Water absorption, 80mil	8.5 / *	%	Sim. to ISO 62

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Density	1140 / -	kg/m <sup>3</sup>	ISO 1183
Density of melt	980	kg/m <sup>3</sup>	-
<b>Injection</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Recommended	yes	-	-
Drying Temperature	≥80	°C	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.05	%	-
Melt Temperature Optimum	290	°C	-
Min. melt temperature	280	°C	-
Max. melt temperature	300	°C	-
Max. screw tangential speed	0.4 / *	m/s	-
Mold Temperature Optimum	70	°C	-
Min. mold temperature	50	°C	-
Max. mold temperature	90	°C	-
Hold pressure range	50 - 100	MPa	-
Hold pressure time	4	s/mm	-
Ejection temperature	190	°C	-
<b>Extrusion</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Temperature	≤80	°C	-
Drying Time, Dehumidified Dryer	4 - 6	h	-
Processing Moisture Content	≤0.05	%	-
Melt Temperature Optimum	285	°C	-
Melt Temperature Range	280 - 290	°C	-

Characteristics			
Processing	<ul style="list-style-type: none"> <li>• Injection Molding</li> <li>• Film Extrusion</li> <li>• Profile Extrusion</li> </ul>	<ul style="list-style-type: none"> <li>• Sheet Extrusion</li> <li>• Other Extrusion</li> <li>• Coating</li> </ul>	<ul style="list-style-type: none"> <li>• Casting</li> </ul>
Delivery form	<ul style="list-style-type: none"> <li>• Pellets</li> </ul>		
Additives	<ul style="list-style-type: none"> <li>• Release agent</li> </ul>		
Special characteristics	<ul style="list-style-type: none"> <li>• Heat stabilized or stable to heat</li> </ul>		
Regional Availability	<ul style="list-style-type: none"> <li>• North America</li> <li>• Europe</li> </ul>	<ul style="list-style-type: none"> <li>• Asia Pacific</li> <li>• South and Central America</li> </ul>	<ul style="list-style-type: none"> <li>• Near East/Africa</li> <li>• Global</li> </ul>

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

### Asia Pacific

TEL: +86 0769-82339888 / 87798999

### Europe/Middle East/Africa




# DuPont™ Zytel® E51HSB NC010


## NYLON RESIN

### Diagrams

#### Viscosity-shear rate




#### Shearstress-shear rate



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Stress-strain (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Stress-strain (cond.)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Secant modulus-strain (dry)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Secant modulus-strain (cond.)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

Specific volume-temperature (pvT)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

Asia Pacific

TEL: +86 0769-82339888 / 87798999

Europe/Middle East/Africa





# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✗ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

#### Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

#### Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✓ Ethanol (23 °C)

#### Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

#### Ketones

- ✓ Acetone (23 °C)

#### Ethers

- ✓ Diethyl ether (23 °C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)

#### Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5 (60 °C)
- ✓ ISO 1817 Liquid 2 - M15E4 (60 °C)
- ✓ ISO 1817 Liquid 3 - M3E7 (60 °C)
- ✓ ISO 1817 Liquid 4 - M15 (60 °C)
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23 °C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23 °C)



# DuPont™ Zytel® E51HSB NC010

## NYLON RESIN

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✗ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✗ Zinc Chloride solution (50% by mass) (23°C)

### Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✗ DOT No. 4 Brake fluid (130°C)
- ✗ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✗ Water (90°C)
- ✗ Phenol solution (5% by mass) (23°C)

#### Symbols used:

✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

#### Asia Pacific

TEL: +86 0769-82339888 / 87798999

#### Europe/Middle East/Africa

