

# DuPont™ Zytel® FG151L NC010

## NYLON RESIN

### Product Information

DuPont™ Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

**Zytel® FG151L is a lubricated polyamide 612 resin for injection molding. It has been developed for consideration into applications in contact with food.**

#### FOOD CONTACT

This product is manufactured according to Good Manufacturing Practice (GMP) principles and generally accepted in food contact applications in Europe and the USA when meeting applicable use conditions. For details, individual compliance statements are available from your DuPont representative.

General information	Value	Unit	Test Standard
Resin Identification	PA612	-	ISO 1043
Part Marking Code	PA612	-	ISO 11469
Rheological properties	dry / cond	Unit	Test Standard
Molding shrinkage, parallel	1.3 / -	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4 / -	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	2400 / 1700	MPa	ISO 527-1/-2
Yield stress	62 / 54	MPa	ISO 527-1/-2
Yield strain	4.5 / 18	%	ISO 527-1/-2
Nominal strain at break	17 / >50	%	ISO 527-1/-2
Flexural Modulus	2100 / 1440	MPa	ISO 178
Charpy impact strength			ISO 179/1eU
73°F	N / N	kJ/m <sup>2</sup>	
-22°F	N / 40	kJ/m <sup>2</sup>	
Charpy notched impact strength			ISO 179/1eA
73°F	3.5 / 4	kJ/m <sup>2</sup>	
-22°F	3.5 / 3	kJ/m <sup>2</sup>	
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature, 18°F/min	218 / *	°C	ISO 11357-1/-3
Glass transition temperature, 18°F/min	65 / 50	°C	ISO 11357-1/-2
Temp. of deflection under load			ISO 75-1/-2
260 psi	62 / *	°C	
65 psi	135 / *	°C	
Vicat softening temperature, 90°F/h, 11 lbf	181 / *	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion			ISO 11359-1/-2
normal	120 / *	E-6/K	
Normal, -40-23°C	90 / *	E-6/K	
Normal, 55-160°C	180 / *	E-6/K	
Parallel, -40-23°C	90 / *	E-6/K	
Parallel, 55-160°C	160 / *	E-6/K	
RTI, electrical			UL 746B
30mil	105 / *	°C	
60mil	105 / *	°C	
120mil	105	°C	
RTI, impact			UL 746B
30mil	65	°C	
60mil	65 / *	°C	
120mil	65	°C	

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com



# DuPont™ Zytel® FG151L NC010

## NYLON RESIN

			UL 746B
RTI, strength			
30mil	65	°C	
60mil	65 / *	°C	
120mil	65	°C	
<b>Flammability</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Burning Behav. at 60mil nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *	-	UL 94
Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.86 / *	mm	IEC 60695-11-10
UL recognition	yes / *	-	UL 94
FMVSS Class	SE	-	ISO 3795 (FMVSS 302)
<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Humidity absorption, 80mil	1.3 / *	%	Sim. to ISO 62
Water absorption, 80mil	3 / *	%	Sim. to ISO 62
Density	1060 / -	kg/m <sup>3</sup>	ISO 1183
<b>VDA Properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Emission of organic compounds	3.9	µgC/g	VDA 277
<b>Injection</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Recommended	yes	-	-
Drying Time, Dehumidified Dryer	2 - 4	h	-
Processing Moisture Content	≤0.15	%	-
Melt Temperature Optimum	250	°C	-
Min. melt temperature	230	°C	-
Max. melt temperature	290	°C	-
Min. mold temperature	50	°C	-
Max. mold temperature	90	°C	-
<b>Extrusion</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Drying Temperature	75 - 80	°C	-
Drying Time, Dehumidified Dryer	3 - 4	h	-
Processing Moisture Content	≤0.06	%	-
Melt Temperature Optimum	240	°C	-
Melt Temperature Range	235 - 250	°C	-
<b>Characteristics</b>			
Processing	• Injection Molding		
Delivery form	• Pellets		
Additives	• Release agent		
Special characteristics	• Light stabilized or stable to light		
Regional Availability	• North America	• Asia Pacific	• Near East/Africa
	• Europe	• South and Central America	• Global

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com



# DuPont™ Zytel® FG151L NC010

## NYLON RESIN

### Chemical Media Resistance

#### Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✗ Hydrochloric Acid (36% by mass) (23 °C)
- ✗ Nitric Acid (40% by mass) (23 °C)
- ✗ Sulfuric Acid (38% by mass) (23 °C)
- ✗ Sulfuric Acid (5% by mass) (23 °C)
- ✗ Chromic Acid solution (40% by mass) (23 °C)

#### Bases

- ✗ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

#### Alcohols

- ✓ Isopropyl alcohol (23 °C)
- ✓ Methanol (23 °C)
- ✓ Ethanol (23 °C)

#### Hydrocarbons

- ✓ n-Hexane (23 °C)
- ✓ Toluene (23 °C)
- ✓ iso-Octane (23 °C)

#### Ketones

- ✓ Acetone (23 °C)

#### Ethers

- ✓ Diethyl ether (23 °C)

#### Mineral oils

- ✓ SAE 10W40 multigrade motor oil (23 °C)
- ✗ SAE 10W40 multigrade motor oil (130 °C)
- ✗ SAE 80/90 hypoid-gear oil (130 °C)
- ✓ Insulating Oil (23 °C)
- ✗ Motor oil OS206 304 Ref.Eng.Oil, ISP (135 °C)
- ✗ Automatic hypoid-gear oil Shell Donax TX (135 °C)

#### Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5 (60 °C)
- ✓ ISO 1817 Liquid 2 - M15E4 (60 °C)
- ✓ ISO 1817 Liquid 3 - M3E7 (60 °C)
- ✓ ISO 1817 Liquid 4 - M15 (60 °C)

Revised: 2017-02-02

Page: 3 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



# DuPont™ Zytel® FG151L NC010

## NYLON RESIN

- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ✗ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)
- ✓ Diesel EN 590 (100°C)

### Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✗ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

### Other

- ✓ Ethyl Acetate (23°C)
- ✗ Hydrogen peroxide (23°C)
- ✗ DOT No. 4 Brake fluid (130°C)
- ✗ Ethylene Glycol (50% by mass) in water (108°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ 50% Oleic acid + 50% Olive Oil (23°C)
- ✓ Water (23°C)
- ✗ Water (90°C)
- ✗ Phenol solution (5% by mass) (23°C)

### Symbols used:

- ✓ possibly resistant

Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).

- ✗ not recommended - see explanation

Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

#### Asia Pacific

TEL: +86 0769-82339888 / 87798999

#### Europe/Middle East/Africa



# DuPont™ Zytel® FG151L NC010

## NYLON RESIN

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

Revised: 2017-02-02

Page: 5 of 5

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

#### North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: [fumei@foomx.com](mailto:fumei@foomx.com)

#### Asia Pacific

TEL: +86 0769-82339888 / 87798999

#### Europe/Middle East/Africa



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.