

DuPont™ Zytel® LC6601 BK551

NYLON RESIN

Product Information

DuPont™ Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

Zytel® LC6601 BK551 is a toughened, polyamide 612 resin plasticized for improved flexibility in extrusion applications.

General information	Value	Unit	Test Standard
Resin Identification	PA612-IP	-	ISO 1043
Part Marking Code	PA612-IP	-	ISO 11469
Mechanical properties	dry / cond	Unit	Test Standard
Yield stress	32 / -	MPa	ISO 527-1/-2
Yield strain	32 / -	%	ISO 527-1/-2
Nominal strain at break	>50 / -	%	ISO 527-1/-2
Strain at Break, 23°C, 50mm/min	200 / -	%	ISO 527-1/-2
Flexural Modulus	850 / -	MPa	ISO 178
Thermal properties	dry / cond	Unit	Test Standard
Melting temperature, 18°F/min	215 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 260 psi	45 / *	°C	ISO 75-1/-2
Flammability	Value	Unit	Test Standard
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<100	mm/min	ISO 3795 (FMVSS 302)
Other properties	dry / cond	Unit	Test Standard
Density	1020 / -	kg/m ³	ISO 1183
Extrusion	Value	Unit	Test Standard
Drying Temperature	75 - 80	°C	-
Drying Time, Dehumidified Dryer	3 - 4	h	-
Processing Moisture Content	≤0.06	%	-
Melt Temperature Optimum	240	°C	-
Melt Temperature Range	230 - 245	°C	-

Characteristics			
Processing	<ul style="list-style-type: none"> • Injection Molding • Film Extrusion 	<ul style="list-style-type: none"> • Profile Extrusion • Sheet Extrusion 	<ul style="list-style-type: none"> • Other Extrusion
Delivery form	<ul style="list-style-type: none"> • Pellets 		
Special characteristics	<ul style="list-style-type: none"> • Heat stabilized or stable to heat 		
Regional Availability	<ul style="list-style-type: none"> • North America • Europe 	<ul style="list-style-type: none"> • Asia Pacific • South and Central America 	<ul style="list-style-type: none"> • Near East/Africa • Global

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com

