

# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

## NYLON RESIN

**产品**

DuPont™ Zytel® LCPA long chain polyamide resins provide an innovative and growing portfolio of flexible polymers with excellent thermal, chemical, and hydrolysis resistance. The diverse selection of Zytel® LCPA grades is targeted for a range of performance characteristics, balancing temperature resistance, flexibility and low permeation.

Zytel® LCBM6301 BK010 is a toughened polyamide 612 resin for blow molding applications.

总说明	数值	单位	测试标准
树脂鉴别	PA612-HI	-	ISO 1043
产品标识码	PA612-HI	-	ISO 11469
机械性能	干态/调节后	单位	测试标准
拉伸模量	1100 / 750	MPa	ISO 527-1/-2
屈服应力	32 / 29	MPa	ISO 527-1/-2
屈服伸长率	12 / 30	%	ISO 527-1/-2
名义断裂伸长率	>50 / >50	%	ISO 527-1/-2
断裂应变, 23°C	100 / 285	%	ISO 527-1/-2
简支梁缺口冲击强度			ISO 179/1eA
+23°C	35 / 80	kJ/m <sup>2</sup>	
-30°C	13 / 12	kJ/m <sup>2</sup>	
热性能	干态/调节后	单位	测试标准
熔融温度, 10°C/min	216 / *	°C	ISO 11357-1/-3
热变形温度			ISO 75-1/-2
1.80 MPa	47 / *	°C	
0.45 MPa	83 / *	°C	
燃烧性能	数值	单位	测试标准
FMVSS Class	B	-	ISO 3795 (FMVSS 302)
燃烧速率, 厚度: 1毫米	<100	mm/min	ISO 3795 (FMVSS 302)
其它性能	干态/调节后	单位	测试标准
吸湿性, 2mm	0.65 / *	%	类似ISO 62
密度	1010 / -	kg/m <sup>3</sup>	ISO 1183

**典型数据**

加工方法	• 注塑	• 吹塑
供货形式	• 粒料	
特殊性能	• 热稳定、耐热的	




# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)


## NYLON RESIN

图表

粘度 - 剪切速度



剪切应力 - 剪切速度



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com


Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

## NYLON RESIN

应力 - 应变. (干)



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

Asia Pacific

TEL: +86 0769-82339888 / 87798999


Europe/Middle East/Africa



# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

NYLON RESIN


应力 - 应变. (湿)



# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

## NYLON RESIN


正割模量 - 应变. (干)



# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

NYLON RESIN

正割模量 - 应变. (湿)



修订：2018-02-27

Page: 6 of 8

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Asia Pacific

Europe/Middle East/Africa

DONGGUAN FUMEI PLASTICS CO.,LTD.

TEL: +86 0769-82339888 / 87798999

EMAIL: fumei@foomx.com


Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.




# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

## NYLON RESIN

拉伸模量 - 温度(干)



拉伸模量 - 温度(湿)



以上是初步数据，可能会根据后面批次的测试数据产生变动。

联系杜邦以获得材料安全物性数据表、一般指南和/或其他关于排风、处理、清洗、干燥等的相关信息。除非特别指定，ISO机械性能测试样条厚度为4mm (Hytel® 2mm英寸)，IEC电性能测试样品厚度为2mm，所有的ASTM性能测试样条厚度为3.2mm，测试温度为23°C。

修订：2018-02-27

Page: 7 of 8

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

DONGGUAN FUMEI PLASTICS CO.,LTD.

EMAIL: fumei@foomx.com

Asia Pacific

TEL: +86 0769-82339888 / 87798999

Europe/Middle East/Africa

Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



# DuPont™ Zytel® LCBM6301 BK010 (Preliminary Data)

## NYLON RESIN

这里阐明的信息是免费提供的，基于杜邦认为可靠的技术数据且，在材料性能的通常范围内。仅供具有专业技能的人使用，由其自行判断和承担风险。

这些数据不可以用作以建立技术说明规范，或者作为设计依据单独使用；我们提供处理预警信息是基于我们理解使用者会自行判断其特殊的使用条件不会对其产生健康或者安全危害。

由于产品使用和废弃的条件超出了本公司的控制范围，本公司对于本信息的使用不做任何保证，不论明示或暗示，亦不承担任何责任。

对于任何材料，制定规范前必须在终端使用条件下进行评估。

这里的任何信息不能作为使用专利或者侵犯专利权的许可。

**警告：**不要用于涉及永久植入人体的医疗应用。

如果需要其他医疗方面的应用，请联系杜邦销售代表并阅读医疗应用警告H-50103-5.

Copyright© 2017杜邦公司版权所有杜邦椭圆形商标，DuPont™, The miracles of science™ 以及所有标有® 或™ 的产品是杜邦公司或其分支机构关联公司的商标或者注册商标。

